

Jewelry Molding Rubber Gold Label®



Technical Datasheet





Name Gold Label®

Shore A Hardness	37.3
Vulcanizes at	307°F / 152°C
Rubber Shrinkage	2.1%
Break Elongation	706%
Break Tensile Strength	Very Strong 2,475 psi 13.9 n/mm²
Break Tear Strength	l 34 lb./in. 23.4 n/mm²
Uses	Strong, Flexible Molds

^{*}Shrinkage rates given are for the rubber mold itself. Final casting shrinkage rates depend on mouldmakers and caster's skill, knowledge, precision and attention to detail.

Net Weight:

5 lb / 2.27 kg & 50 lb / 22.7 kg rolls

Castaldo Gold Label® comes packed in 50 lb / 22.7 kg strong and convenient roll dispenser boxes and 5 lb / 2.27 kg convenient rolls packed in consumer oriented tubes.

Castaldo Gold Label® is lined with golden coloured cloth on oneside and lightly dusted on the other side. Dust does not need to be cleaned off and does not act as a separator or interfere with proper lamination and vulcanisation.

Complete instructions are enclosed in each box.

Easy to handle and to roll out the rubber. Keeps the rubber neat, clean and fresh in the roll format.