



HI-TECH EQUIPMENT FOR PRECIOUS MATERIALS

BUKO NV
Engelse Wandeling 5
8500 Kortrijk
Belgium

T: + 32 56 22 05 49
E: info@buko.be

F: +32 56 22 90 21
W: www.buko.be

BTW - TVA - VAT : BE 0405 319 448

ANTITARNISH-A-100

Antitarnish - A-100 is used to apply a protective layer on silver, copper, brass, etc. This protective layer helps your jewelry oxidize more slowly.

Equipment :

- Beaker made of polypropylene or glass
- Heating: quartz element + temperature controller
- Movement: the piece must be sufficiently moved during the process
- Exhaust is not necessary but recommended

Application:

Step 1: Immerse your item in a 50°C warm Antitarnish-A-100 bath

Step 2: Move the item regularly during the process

Step 3: Remove the item from the bath after 5 to 8 minutes

Step 4: Rinse the piece for 1 minute in a 50°C warm demineralized water bath

Step 5: Dry the piece using warm air at approximately 60°C

Ensure adequate heating: the specified temperature must be strictly followed.

If the product becomes too hot (above 55°C), it will turn cloudy and can no longer be used.

Antitarnish-A-100 contains no dangerous or harmful substances.

The product has a minimum shelf life of 24 months in a closed container.

Store in a cool, frost-free place.

