

Jewelry Molding Rubber White Label®



Technical Datasheet



Name	White Label®
Shore A Hardness	42.1
Vulcanizes at	307°F / 152°C
Rubber Shrinkage	2.3%
Break Elongation	688%
Break Tensile Strength	Very Strong 2,215 psi 15.3 n/mm²
Break Tear Strength	137 lb./in. 24 n/mm²
Uses	Strong, Firm Molds

^{*}Shrinkage rates given are for the rubber mold itself. Final casting shrinkage rates depend on moldmakers and caster's skill, knowledge, precision and attention to detail.

Net Weight:

5 lb / 2.27 kg & 50 lb / 22.7 kg rolls

Castaldo White Label® comes packed in 50 lb / 22.7 kg strong and convenient roll dispenser boxes and 5 lb / 2.27 kg convenient rolls packed in consumer oriented tubes.

Castaldo White Label® is lined with white coloured cloth on oneside and lightly dusted on the other side. Dust does not need to be cleaned off and does not act as a separator or interfere with proper lamination and vulcanisation.

Complete instructions are enclosed in each box.

Easy to handle and to roll out the rubber. Keeps the rubber neat, clean and fresh in the roll format.